



CTI-150

齐聚物 · 单体 · 光引发剂 · 助剂

免责声明

All products in the text marked with are trademarks of the U-sunny .The information on product specifications provided herein is only binding to the extent confirmed by U-sunny in a written Sales Agreement. U-sunny expressly disclaims any responsibility for the suitability of the products for any specific or particular purposes intended by the user .Suggestions or the use and application of the products and guide formulations are given for information purposes only and without commitment. Such suggestions do not release U-sunny customers from testing the products as to their suitability for the customers intended processes and purposes. U-sunny does not assume any liability or risk involved in the use of its products as the conditions of use are beyond its control. The user of the products is solely responsible for compliance with all laws and regulations applying to the use of the products .including intellectual property rights of third parties.

CTI-150 阳离子热引发剂

MW: 275

Density,g/cm³: 1.350

Curing condition : 90-150°C 5-40min

Form: 白色粉末

Viscosity at 25°C (50%inPC) : 10cps

CTI-150 是一款封闭型硫鎓锑酸盐阳离子引发剂，是一款极具性价比的产品，配合 EAP-6S 稳定剂在添加有机溶剂的配方里同样可以常温 稳定储存 3-6 个月，当达到解封温度后又能快速固化反应。对于各类型环氧树脂及活性稀释剂都有很好的固化效果。引发剂添加量少，涂 膜交联强度高，耐湿热性优异。可以单独使用加热固化交联，或作为 光固化引发剂的有效补充，在不见光条件或者特厚涂 膜作为双固化应 用。在胶黏剂、电子封装、3D 打印，环氧复合成型及高要求的印刷油 墨等行业广泛应用，固化膜不黄变，无游离酸残 留。