



## Irgacure-250 光引发剂

齐聚物 · 单体 · 光引发剂 · 助剂

### 免责声明

All products in the text marked with are trademarks of the U-sunny .The information on product specifications provided herein is only binding to the extent confirmed by U-sunny in a written Sales Agreement. U-sunny expressly disclaims any responsibility for the suitability of the products for any specific or particular purposes intended by the user .Suggestions or the use and application of the products and guide formulations are given for information purposes only and without commitment. Such suggestions do not release U-sunny customers from testing the products as to their suitability for the customers intended processes and purposes. U-sunny does not assume any liability or risk involved in the use of its products as the conditions of use are beyond its control. The user of the products is solely responsible for compliance with all laws and regulations applying to the use of the products. including intellectual property rights of third parties.

### Irgacure-250

4-异丁基苯基-4'-甲基苯基碘鎓六氟磷酸盐

(4-Methylphenyl) [4-(2-methylpropyl)phenyl] iodonium hexafluorophosphate

Density,g/cm<sup>3</sup>: 1.485

MW: 496.2

Viscosity at 25°C: 480cps

Active Constituent: : 75% propylene carbonate solution

Absorption Wavelength: 245nm

应用: 碘鎓盐光引发剂光解可同时发生均裂和异裂, 既产生超强酸, 又产生活性自由基。因此碘鎓盐除可引发阳离子光聚合外, 还可同时引发自由基聚合。具有优异的非黄变性、固化后无苯释放且固化性能优异等特

点。Irgacue 250 可单独使用或者与适当的光敏剂混合用于 UV 固化油墨, 胶粘剂, 图形艺术成像, 光刻胶, 纸张、金属和塑料表面的清漆。非常适用于高环保要求, 高性能的阳离子固化清漆和有色体系。