



PAS-33 光敏增感剂

齐聚物 · 单体 · 光引发剂 · 助剂

免责声明

All products in the text marked with are trademarks of the U-sunny .The information on product specifications provided herein is only binding to the extent confirmed by U-sunny in a written Sales Agreement. U-sunny expressly disclaims any responsibility for the suitability of the products for any specific or particular purposes intended by the user .Suggestions or the use and application of the products and guide formulations are given for information purposes only and without commitment. Such suggestions do not release U-sunny customers from testing the products as to their suitability for the customers intended processes and purposes. U-sunny does not assume any liability or risk involved in the use of its products as the conditions of use are beyond its control. The user of the products is solely responsible for compliance with all laws and regulations applying to the use of the products. including intellectual property rights of third parties.

PAS-33 葷醜衍生物

Polymer solids % by weight: 100%

Colour, Gardner: 5

Viscosity at 25°C, cPa.s: 150

Density, g/cm3: 1.02

Absorption Wavelength: 410nm

应用: PAS-33 增感剂主吸收峰值在 410nm, 最长可延长至 470nm 所以是极为有效的阳离子增感剂。以 PAS-33 引发的阳离子固化体系其固化速率已经完全可以和自由基体系相同。相溶性好, 性价比高, 在阳离子有色体系固化, 及厚膜深层固化应用方面起着更加积极的作用。