

T-7205

聚氨酯丙烯酸酯 UV 树脂

两官能度聚氨酯丙烯酸酯

| | |
|----------------------------|-------------|
| Polymer solids % by weight | 100% |
| Colour, Gardner | 1 |
| Acid value,mg KOH/g | max. 2 |
| Viscosity at 60°C,mPa.s | 35000-55000 |
| Density,g/cm ³ | 1.12 |

应用：T-7205 树脂具有低收缩、高成膜强度，耐酸、碱性非常优异。应用于塑胶，金属及 PET 塑料片材等表面油墨，转印油墨。于真空镀底漆应用具有优异的水煮性能。

| | | |
|-----------------------------|-----------------------|------------------------|
| 深圳市优阳科技有限公司 | | |
| Telephone ++86 755 89471001 | Fax ++86 755 89471025 | E-mail: uyuv88@163.com |

All products in the text marked with are trademarks of the U-sunny .The information on product specifications provided herein is only binding to the extent confirmed by U-sunny in a written Sales Agreement. U-sunny expressly disclaims any responsibility for the suitability of the products for any specific or particular purposes intended by the user .Suggestions on the use and application of the products and guide formulations are given for information purposes only and without commitment. Such suggestions do not release U-sunny customers from testing the products as to their suitability for the customers intended processes and purposes. U-sunny does not assume any liability or risk involved in the use of its products as the conditions of use are beyond its control. The user of the products is solely responsible for compliance with all laws and regulations applying to the use of the products. including intellectual property rights of third parties.