

## Trust 7210

### Di-functional Aliphatic Urethane Acrylates

两官能度聚氨酯丙烯酸酯

Tg(°C)	-20
MW(GPC)	5500
Elongation at Break%	70
Polymer solids % by weight	100%
Colour, Gardner	2
Acid value,mg KOH/g	max. 1
Viscosity at 25°C,mPa.s	55000-70000
Density,g/cm <sup>3</sup>	1.10

应用：T-7210 树脂推荐用于高柔韧要求的 FPC 线路板印刷，光刻胶，IMD 丝网油墨，涂料。柔韧性好，成膜强度高、弹性好，可耐吸塑成型瞬间高温热冲击性，收缩率低。耐水性及耐化性好。

深圳市优阳科技有限公司

Telephone ++86 755 89471001    Fax ++86 755 89471025    E-mail: uyuv88@163.com

All products in the text marked with are trademarks of the U-sunny .The information on product specifications provided herein is only binding to the extent confirmed by U-sunny in a written Sales Agreement. U-sunny expressly disclaims any responsibility for the suitability of the products for any specific or particular purposes intended by the user .Suggestions or the use and application of the products and guide formulations are given for information purposes only and without commitment. Such suggestions do not release U-sunny customers from testing the products as to their suitability for the customers intended processes and purposes. U-sunny does not assume any liability or risk involved in the use of its products as the conditions of use are beyond its control. The user of the products is solely responsible for compliance with all laws and regulations applying to the use of the products. including intellectual property rights of third parties.