



Uyracure-180

齐聚物 · 单体 · 光引发剂 · 助剂

免责声明

All products in the text marked with are trademarks of the U-sunny .The information on product specifications provided herein is only binding to the extent confirmed by U-sunny in a written Sales Agreement. U-sunny expressly disclaims any responsibility for the suitability of the products for any specific or particular purposes intended by the user .Suggestions or the use and application of the products and guide formulations are given for information purposes only and without commitment. Such suggestions do not release U-sunny customers from testing the products as to their suitability for the customers intended processes and purposes. U-sunny does not assume any liability or risk involved in the use of its products as the conditions of use are beyond its control. The user of the products is solely responsible for compliance with all laws and regulations applying to the use of the products. including intellectual property rights of third parties.

Uyracure-180

4-(苯硫基)苯基二苯基硫鎓六氟锑酸盐

4- (benzene sulfonium)phenyl diphenyl sulfide weng six fluorine antimonate

MW: 580.80

Density,g/cm³: 1.420

Absorption Wavelength: 290nm

Active Constituent: 50%propylene carbonate solution

Viscosity at 25°C: 440cps

三芳基硫鎓六氟锑酸盐因为硫原子可与三个芳环部分共轭，正电荷得到分散，光激发后可发生裂解，产生聚合活性种，具有比磷酸盐更强的反应活性。添加量只需三芳基硫鎓六氟磷酸盐的 40-60% 具有更高的交联硬度，无迁移，无气味，耐温性，及深层固化好等特点。吸收波长 290nm, 兼具高性能和经济性。应用于阳离子固化透明涂层，胶黏剂，LED 封装，油墨等领域。